

### Amendments to the Claims

This listing of claims will replace all prior listings of claims in the application.

#### Listing of Claims

1. (Currently Amended) An aluminum alloy piping material for automotive tubes having excellent corrosion resistance and formability, and which is an annealed material of an aluminum alloy comprising, in mass percent ~~(hereinafter the same)~~, 0.3 to 1.5% of Mn, 0.20% or less of Cu, 0.10 to 0.20% of Ti, more than 0.20% but 0.60% or less of Fe, and 0.50% or less of Si with the balance being aluminum and unavoidable impurities, wherein the aluminum alloy piping material has an average crystal grain size of 100  $\mu$ m or less, and Ti-based compounds having a grain size ~~(circle equivalent diameter, hereinafter the same)~~ of 10  $\mu$ m or more do not exist as an aggregate of two or more serial compounds in a single crystal grain.

2. (Currently Amended) The aluminum alloy piping material ~~for automotive tubes having excellent corrosion resistance and formability~~ according to claim 1, wherein the aluminum alloy further comprises up to 0.4% ~~or less (excluding 0%, hereinafter the same)~~ of Mg.

3. (Currently Amended) The aluminum alloy piping material ~~for automotive tubes having excellent corrosion resistance and formability~~ according to claim 1, wherein the aluminum alloy further comprises at least one of 0.01 to 0.2% of Cr and 0.01 to 0.2% of Zr.

4. (Currently Amended) The aluminum alloy piping material ~~for automotive tubes having excellent corrosion resistance and formability~~ according to claim 1, wherein the

aluminum alloy further comprises at least one of 0.01 to 0.1% of Zn, 0.001 to 0.05% of In, and 0.001 to 0.05% of Sn.

5. (Previously Presented) A method of manufacturing an aluminum alloy piping material for automotive tubes having excellent corrosion resistance and formability, the method comprising hot extruding a billet of the aluminum alloy according to claim 1 into an aluminum alloy tube, cold drawing the aluminum alloy tube, and annealing the cold-drawn product, wherein a reduction ratio of the cold drawing is 30% or more, a total reduction ratio of the hot extrusion and the cold drawing is 99% or more, and a temperature increase rate during the annealing is 200°C/h or more, the reduction ratio being expressed by  $\{(\text{cross-sectional area before forming} - \text{cross-sectional area after forming}) / (\text{cross-sectional area before forming})\} \times 100\%$ .

6. (New) An aluminum alloy piping material for automotive tubes having excellent corrosion resistance and formability and which is an annealed material of an aluminum alloy comprising, in mass percent, 0.3 to 1.5% of Mn, 0.05 to 0.1% of Cu, 0.10 to 0.20% of Ti, more than 0.20% but no more than 0.60% of Fe and 0.50% or less of Si, with the balance being aluminum and unavoidable impurities, the aluminum alloy piping material having an average crystal grain size of 100  $\mu\text{m}$  or less and Ti-based compounds having a grain size of 10  $\mu\text{m}$  or more do not exist as an aggregate of two or more serial compounds in a single crystal grain.

7. (New) The aluminum alloy piping material according to Claim 1, wherein at least 0.22% Fe is present.

8. (New) The aluminum alloy piping material according to Claim 1, wherein at least 0.30% Fe is present.

9. (New) The aluminum alloy piping material according to Claim 6, wherein at least 0.22% Fe is present.

10. (New) The aluminum alloy piping material according to Claim 6, wherein at least 0.30% Fe is present.